



Bitumen 80/100		
	Specification	Test method
Specific gravity @25/25 C	1.01-1.05	D-70
Penetration @25 C	80/100	D-5
Softening point C	45/52	D-36
Ductility @25 C	100 min	D-113
Loss on heating (wt)%	0.5 max	D-6
Drop in penetration after heating %	20 max	D-6 & D-5
Flash point C	225min	D-92
Solubility in CS2 (wt)%	99.5 min	D-4

Spot test

negative

\*A.A.S.H.O.T.10

Bitumen 85/100		
	Specification	Test method
Specific gravity @25/25 C	1.01-1.05	D-70
Penetration @25 C	85/100	D-5
Softening point C	45/52	D-36
Ductility @25 C	100 min	D-113
Loss on heating (wt)%	0.5 max	D-6
Drop in penetration after heating %	20 max	D-6 & D-5
Flash point C	225min	D-92
Solubility in CS2 (wt)%	99.5 min	D-4

Spot test

negative

\*A.A.S.H.O.T.10